



TEST REPORT

Product Name Seamless tube

Applicant Zhangjiagang chewit International co.,Ltd

Manufacturer Zhangjiagang chewit International co.,Ltd

Test Classification Commissioned test




Suzhou Qinghong Testing Technology Co.,Ltd.





Declaration

- 1 The report is valid to be signed by the main tester, reviewer and approver, and the special inspection stamp.
- 2 The specimens should not be involved in legal disputes. Our lab is responsible for the monitoring data of the specimens but not responsible for the source of the specimens. The appeal is unacceptable if the specimens can not be reproduced.
- 3 Our lab is responsible for the authenticity, legality, applicability and scientificity of the report.
- 4 If the customer has objection to the test data in this report, please submit a complaint to our customer service department within 15 days upon reception of this report. It is not accepted if the time limit is exceeded.
- 5 No partial replication can be made without permission. Any unauthorized alteration, forgery, alteration or improper use of this report is illegal, the responsible person will bear relevant legal and economic responsibilities. Our lab reserves the right to pursue legal liability for the above violations.
- 6 The test report without the certification mark (CMA) is only used for scientific research, teaching, and internal quality control, and does not have the role of proof to the society
- 7 The data of the '*' project is provided by the subcontractor accredited by our laboratory.
- 8 Our lab keeps a secret of the report's test data.
- 9 Please pick up the specimens within 30days upon the reception of the report if the specimens are necessary to return to the customers, or else, our lab will deal with them by ourselves accordance with the law.

Test Conclusion

| | | | |
|--------------------|---|---------------|--|
| Product Name | Seamless tube | Model | Seamless tube, 6*1, 10x1, 15*1.5, 22x2, 35x3, 42x3,0 |
| | | Sample No. | 20230105WD001-03~08 |
| Applicant& Add. | Zhangjiagang chewit International co.,Ltd Jinjang Town, Zhangjiagang City, Jiangsu Province | | |
| Manufacturer &Add. | Zhangjiagang chewit International co.,Ltd Jinjang Town, Zhangjiagang City, Jiangsu Province | | |
| Date of Sample | 2023.01.05 | Test Time | 2023.01.05~2023.01.12 |
| Specimen Quantity | 6PCS | Sample Status | Meet test status |
| Environment | Temperature (°C) : 22.8~25.4 Humidity (%RH) : 54~58 | | |
| Check address | No. 2, Commercial Building 27, Heshan Garden, High-tech Zone, Suzhou | | |
| Test Standard | 1. GB/T 10125-2012 artificial atmosphere corrosion test salt spray test 2. Customer technical requirements | | |
| Test Items | Neutral salt spray test | | |
| Test Conclusion | Test the samples according to the customer's technical requirements in accordance with Article 8.0 of GB/T 10125-2012 artificial atmosphere corrosion test salt spray test. The test results refer to page 2 ~ Page 3. <div style="text-align: right;"> Report Date 2023.1.16  </div> | | |
| Remark | --- | | |

Tester 

Checked 

Approved 

Test Conclusion


| No | Test Item | Technical Requirements | Test Conclusion | | Verdict |
|--------|-------------------------|---|-------------------------|--|---------|
| | | | Number | Result | |
| 1 | Neutral salt spray test | According to GB/T 10125-2012 corrosion test in artificial atmosphere salt spray test clause 8.0: Temperature: 35°C; The average settlement rate of the horizontal area of 80cm ² is 1.5mL/h±0.5mL/h; Sodium chloride solution concentration: 50g/L±5g/L; pH value: 6.5~7.2 Test time: 120h Customer technical requirements: No white rust shall appear on the surface of the sample after testing. | 20230105W D001-03~08 | After the test, no white rust appeared on the surface of the sample. | Pass |
| Remark | | — | | | |



----- BLANK BELOW -----

Test Conclusion

Test photos



Erection photograph



Temperature indication

After test photos



20230105WD001-03~08

Test Equipment

| Equipment No. | Equipment Name | Part No./Model | Calibration Validity |
|---------------|---|----------------|----------------------|
| TS-TE-A0137 | Multifunctional salt spray test chamber | ZCMYW-900 | 2023.04.20 |

.....END.....